APPLICATION



If contaminated, use a clay bar to clean. If paint correction is required, do so before application.



Wash and completely dry surfaces to be coated.



Clean the wheel using a 50% IPA (isopropyl alcohol) to water mix in a trigger sprayer. Mist the wheel then wipe down with a microfiber towel.



Wipe on coating by hand using a sponge or coating block. After wiping on wait 30-60 seconds to flash (depending on temp) then buff off with a microfiber towel.



PRODUCT OVERVIEW

brake dust. System X Wheel easily registers to CARFAX with the included QR code sticker to maximize vehicle resale value (US & Canada only).

TECHNICAL DATA

EFFECTIVENESS	Up to 3 years depe
PENCIL HARDNESS	9H
APPLICATION	Wipe on / buff off a
BOTTLE SIZE	20mL, 65mL, 275m
SHELF TIME	18 months from sh
APPEARANCE	Clear / High Gloss
FILM THICKNESS	Up to 0.9 mil
CHEM. RESISTANCE	Outstanding
TEMP. RESISTANCE	> 760°C (1400°F)
SALT SPRAY	(ASTM B117) @ 35°
ADHESION CROSS-CUT TAPE	(ASTM D3359) 5b (0
MANDREL BEND	(ASTM D522) 0% @
ІМРАСТ	(ASTM D2794) 80/8
COVERAGE	180 sq feet (16.7m)
DRY TIME	40 minutes
CURE TIME	Initial cure in 4 hou
UV PROTECTION	Yes



CERTIFIED PROFESSIONAL USE ONLY

REGISTERS WITH CARFAX



ending on environmental factors

application or use HVLP gun with 0.8mm tip and buff off by hand

mL, 4L

hipment date when unopened and stored dry at 13°C (55°F) to 29°C (85°F)

5°C (95°F), 5% salt concentration, > 400 hrs to first signs of corrosion

(0%, none)

@ 180° rotation

/80 in/lbs

n2) per 100mL

ours, full cure in 3 days